

## Lega metallo /Tungsten Alloy

### Caratteristiche fisico/chimiche

#### DATA SHEET

#### OD18D

Typical Applications:	Ballast & Balancing
Ref.cod	ASTM B777-07 Class 3
Nominal Composition:	95% W – 3.5% Ni – 1.5% Fe
Density:	18gm/cm <sup>3</sup>
Hardness:	27 HRC
Elongation:	7%
Ultimate Tensile Strength	870 N/mm <sup>2</sup>
Magnetic Properties:	Weakly Ferro Magnetic