

Lega metallo /Tungsten Alloy

Caratteristiche fisico/chimiche

DATA SHEET

OD19

Typical Applications:	Extrusion Dies Die Casting Components Electro Forging & Upsetting Riveting Dollies
Nominal Composition:	90% W – 4% Ni – 2% Fe – 4% Mo
Density:	17,1gm/cm ³
Hardness:	28 HRC
Elongation:	5%
Ultimate Tensile Strength	870 N/mm ²
Magnetic Properties:	Weakly Ferro Magnetic